

EP1115011

Publication Title:

RADIATION IMAGE SENSOR

Abstract:

Abstract of EP1115011

In a radiation image sensor (2) comprising a scintillator panel (4) and an imaging device (6), the scintillator panel (4) comprises a radiation-transparent substrate (10), a deliquescent scintillator (12) formed on the substrate (10), and an elastic organic film (14) covering the scintillator (12), the scintillator panel (4) and imaging device (6) being bonded to each other with a matching oil (20) interposed therebetween, whereas side wall portions of the scintillator panel (4) and imaging device (6) are firmly attached to each other with a resin (24).

Data supplied from the esp@cenet database - Worldwide

Courtesy of <http://v3.espacenet.com>



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 115 011 A1**

(12)

EUROPEAN PATENT APPLICATION
published in accordance with Art. 158(3) EPC

(43) Date of publication:
11.07.2001 Bulletin 2001/28

(51) Int Cl.7: **G01T 1/20**

(21) Application number: **99925376.8**

(86) International application number:
PCT/JP99/03263

(22) Date of filing: **18.06.1999**

(87) International publication number:
WO 99/66347 (23.12.1999 Gazette 1999/51)

(84) Designated Contracting States:
DE FR GB IT NL SE

- **HOMME, Takuya**
Hamamatsu-shi Shizuoka-ken 435-8558 (JP)
- **SATO, Hiroto**
Hamamatsu-shi Shizuoka-ken 435-8558 (JP)

(30) Priority: **19.06.1998 JP 17308098**

(71) Applicant: **Hamamatsu Photonics K.K.**
Shizuoka-ken 435-8558 (JP)

(74) Representative: **Brown, Kenneth Richard et al**
R.G.C. Jenkins & Co.
26 Caxton Street
London SW1H 0RJ (GB)


(72) Inventors:
• **TAKABAYASHI, Toshio**
Hamamatsu-shi Shizuoka-ken 435-8558 (JP)

(54) RADIATION IMAGE SENSOR

(57) In a radiation image sensor (2) comprising a scintillator panel (4) and an imaging device (6), the scintillator panel (4) comprises a radiation-transparent substrate (10), a deliquescent scintillator (12) formed on the substrate (10), and an elastic organic film (14) covering

the scintillator (12), the scintillator panel (4) and imaging device (6) being bonded to each other with a matching oil (20) interposed therebetween, whereas side wall portions of the scintillator panel (4) and imaging device (6) are firmly attached to each other with a resin (24).

Fig.1



EP 1 115 011 A1

Description

Technical Field

[0001] The present invention relates to a radiation image sensor used for medical X-ray photography and the like.

Background Art

[0002] While X-ray sensitive films have been used in medical and industrial X-ray photography, radiation imaging systems using radiation detecting devices have been coming into wider use from the viewpoint of convenience and their storability of photographed results. In such a radiation imaging system, pixel data caused by two-dimensional radiation are acquired by a radiation detecting device as an electric signal, which is then processed by a processing unit, so as to be displayed onto a monitor.

[0003] Conventionally known as a typical radiation detecting device is one disclosed in WO92/06476. In this radiation detecting device, a scintillator formed on a substrate and an imaging device are bonded together with an adhesive, such that the radiation incident from the substrate side is converted into visible light by the scintillator, so as to be detected.

[0004] Meanwhile, individual columnar crystals of the scintillator formed on the substrate have different heights, thus yielding unevenness, whereby the tip portion of scintillator might collide with the light-receiving surface of imaging device when being bonded to the imaging device, thereby being damaged. Also, when the imaging device and the scintillator are firmly attached to each other with an adhesive, a distortion may occur in the substrate due to temperature changes, thereby causing a damage to columnar crystals of the scintillator. In the case where a cooling type CCD is used for the imaging device in particular, the distortion becomes greater upon drastic temperature changes, whereby the scintillator is more likely to be damaged.

[0005] It is an object of the present invention to provide a radiation image sensor which can prevent the scintillator from being damaged.

Disclosure of the Invention

[0006] The present invention provides a radiation image sensor comprising a scintillator panel and an imaging device; wherein the scintillator panel comprises a radiation-transparent substrate, a scintillator formed on the substrate, and an elastic organic film covering the scintillator; and wherein the scintillator panel and the imaging device are superposed on each other with an optical coupling material interposed therebetween, side wall portions of the scintillator panel and imaging device being firmly attached to each other with a resin.

[0007] According to the present invention, since the

scintillator is covered with an elastic organic film and is superposed onto the imaging device with an optical coupling material interposed therebetween, the impact acting on the scintillator can be alleviated by way of the elastic organic film when bonding the scintillator panel to the imaging device, whereby the scintillator can be prevented from being damaged. Also, even when a distortion is generated in the substrate due to temperature changes, since the scintillator is covered with the elastic organic film, the stress acting on the scintillator according to the distortion of substrate can be alleviated by the elastic organic film, whereby the scintillator can be prevented from being damaged.

[0008] Also, the present invention is characterized in that the scintillator of radiation image sensor has a columnar structure. According to the present invention, since the tip portion of the scintillator having a columnar structure is covered with the elastic organic film, the impact acting on the tip portion of the scintillator having a columnar structure when superposing the scintillator panel onto the imaging device and the stress acting on the scintillator according to the distortion caused by temperature changes can be alleviated, whereby the tip portion of the scintillator having a columnar structure can be prevented from being damaged.

Brief Description of the Drawings

[0009]

Fig. 1 is a sectional view of the radiation image sensor in accordance with an embodiment of the present invention;

Fig. 2A is a view showing a step of making a scintillator panel in accordance with an embodiment of the present invention;

Fig. 2B is a view showing a step of making the scintillator panel in accordance with an embodiment of the present invention;

Fig. 2C is a view showing a step of making the scintillator panel in accordance with an embodiment of the present invention;

Fig. 3A is a view showing a step of making the scintillator panel in accordance with an embodiment of the present invention; and

Fig. 3B is a view showing a step of making the scintillator panel in accordance with an embodiment of the present invention.

Best Mode for Carrying Out the Invention

[0010] In the following, with reference to Figs. 1 to 3B, embodiments of the present invention will be explained. Fig. 1 is a sectional view of a radiation image sensor 2 in accordance with an embodiment of the present invention. As shown in Fig. 1, the radiation image sensor 2 has a configuration in which a scintillator panel 4 and an imaging device 6 are bonded to each other and are ac-

commodated in a ceramic case 8.

[0011] Here, one surface of a substrate 10 made of Al in the scintillator panel 4 is formed with a scintillator 12, having a columnar structure, for converting incident radiation into visible light. As the scintillator 12 CsI doped with TI is used. All surfaces of the scintillator 12 formed on the substrate 10, together with the substrate 10, are covered with a first polyparaxylylene film (first organic film) 14 having an elasticity, whereas the surface of first polyparaxylylene film 14 on the scintillator 12 side is formed with an SiO₂ film (transparent inorganic film) 16. Further, the surface of SiO₂ film 16 and the surface of the part of first polyparaxylylene film 14 not formed with the SiO₂ film 16 on the substrate 10 side are formed with a second polyparaxylylene film (second organic film) 18, whereby all surfaces are covered with the second polyparaxylylene film 18.

[0012] On the other hand, the imaging device 6 is attached to the scintillator panel 4 on the scintillator 12 side with a silicone resin layer 20, as a matching oil, interposed therebetween, whereas the bottom part of imaging device 6 is accommodated in a cavity portion 8a of the ceramic case 8. As the matching oil, an optical coupling material such as a silicone potting gel exemplified by Sylgard® available from Dow Corning Corporation is used. Further, side wall portions of the scintillator panel 4 and imaging device 6 are fixed to each other by a resin 24 for protecting a bonding wire 22 and fixing the scintillator plate 4 to the ceramic case 8.

[0013] With reference to Figs. 2A to 3B, steps of making the scintillator panel 4 will now be explained. On one surface of a rectangular substrate 10 (having a thickness of 0.5 mm) made of Al, such as the one shown in Fig. 2A, columnar crystals of TI-doped CsI are grown by vapor deposition method, whereby the scintillator 12 is formed by a thickness of 200 μm (see Fig. 2B).

[0014] Since CsI forming the scintillator 12 is high in moisture absorbency so that it will deliquesce by absorbing vapor in the air if left exposed, the first polyparaxylylene film 14 is formed by CVD method in order to prevent this from occurring. Namely, the substrate 10 formed with the scintillator 12 is put into a CVD apparatus, so as to form the first polyparaxylylene film 14 by a thickness of 10 μm. As a consequence, the first polyparaxylylene film 14 is formed on all surfaces of the scintillator 12 and substrate 10 (see Fig. 2C). Since the tip portion of scintillator 12 is uneven, the first polyparaxylylene film 14 also functions to flatten the tip portion of scintillator 12.

[0015] Subsequently, the SiO₂ film 16 is formed on the surface of first polyparaxylylene film 14 on the scintillator 12 side with a thickness of 200 nm by sputtering (see Fig. 3A). The SiO₂ film 16 is formed in an area covering the scintillator 12, since it is aimed at improving the moisture resistance of scintillator 12. Since the tip portion of scintillator 12 is flattened by the first polyparaxylylene film 14 as mentioned above, the SiO₂ film can be formed thinner (with a thickness of 100 nm to 300 nm)

so that the output light quantity would not decrease.

[0016] Further, the second polyparaxylylene film 18 for preventing the SiO₂ film 16 from peeling is formed with a thickness of 10 μm by CVD method on the surface of SiO₂ film 16 and the surface of first polyparaxylylene film 14 not formed with the SiO₂ film 16 on the substrate 10 side (see Fig. 3B). When this step is completed, the making of scintillator panel 4 ends.

[0017] Thereafter, the imaging device 6 is attached to the scintillator panel 4 on the scintillator 12 side with the silicone resin layer 20 interposed therebetween. Also, the bottom part of the imaging device 6 attached to the scintillator panel 4 is accommodated in the cavity portion 8a of ceramic case 8, whereas a pad portion of the imaging device 6 and a lead pin secured to the ceramic case 8 are electrically connected to each other with a bonding wire 22. Then, for protecting the bonding wire 22 and securing the scintillator plate 4 to the ceramic case 8, side wall portions of the scintillator panel 4 and imaging device 6 are fixed with the resin 24. When this step is completed, the making of the radiation image sensor 2 shown in Fig. 1 ends.

[0018] In the radiation image sensor 2 in accordance with this embodiment, since the scintillator 12 is covered with the first polyparaxylylene film 14 and is attached to the imaging device 6 with the silicone resin 20 interposed therebetween, the impact acting on the tip portion of scintillator 12 when bonding the scintillator panel 4 to the imaging device 6 can be alleviated by the first polyparaxylylene film 14, whereby the tip portion of scintillator 12 can be prevented from being damaged. Also, even when a distortion is generated in the substrate 10 due to temperature changes, since the scintillator 12 is covered with the first polyparaxylylene film 14, the stress acting on the scintillator 12 according to the distortion of substrate 10 can be alleviated by the first polyparaxylylene film 14, whereby the scintillator 12 can be prevented from being damaged.

[0019] Also, since the side walls of scintillator panel 4 and imaging device 6 are fixed with the resin 24, the connection between scintillator panel 4 and imaging device 6 can be made firm.

[0020] Though the silicone resin 20 is used as the matching oil (optical coupling material) in the above-mentioned embodiment, it is not restrictive; and epoxy resin, silicone oil, and the like may also be used.

[0021] Though the side wall portions of scintillator panel 4 and imaging device 6 are fixed with one piece of resin 24 in order to protect the bonding wire 22 and secure the scintillator plate 4 to the ceramic case 8, separate resins may be used for protecting the bonding wire 22 and for securing the scintillator plate 4 to the ceramic case 8.

[0022] Also, though the SiO₂ film is used as the transparent inorganic film 16, it is not restrictive; and inorganic films made from Al₂O₃, TiO₂, In₂O₃, SnO₂, MgO, MgF₂, LiF, CaF₂, SiNO, AgCl, SiN and the like may also be used.

[0023] Though CsI(Tl) is used as the scintillator 12 in the above-mentioned embodiment, it is not restrictive; and CsI(Na), NaI(Tl), LiI(Eu), KI(Tl), and the like may also be used.

[0024] Though a substrate made of Al is used as the substrate 10 in the above-mentioned embodiment, any substrate can be used as long as it has a favorable X-ray transmissivity, whereby substrates such as those made of amorphous carbon mainly composed of carbon, those made of C (graphite), those made of Be, those made of SiC, and the like may also be used.

[0025] Though the scintillator 12 is covered with the first polyparaxylylene film 14, SiO₂ film 16, and second polyparaxylylene film 18 in the above-mentioned embodiment, it may be covered with the first polyparaxylylene film 14 alone or with the first polyparaxylylene film 14 and SiO₂ film 16. Since the first polyparaxylylene film 14 in contact with the scintillator 12 has an elasticity, the scintillator 12 can also be prevented from being damaged in this case as in the radiation image sensor 2 in accordance with the above-mentioned embodiment.

[0026] Though the imaging device 6 is used in the above-mentioned embodiment, a cooling type imaging device (C-CCD) may also be used. In this case, since the stress acting on the scintillator increases upon drastic temperature changes, the scintillator damage prevention effect of the elastic organic film becomes greater.

[0027] As the polyparaxylylene film in the above-mentioned embodiment, not only polyparaxylylene but also polymonochloroparaxylylene, polydichloroparaxylylene, polytrichloroparaxylylene, polyfluoroparaxylylene, polydimethylparaxylylene, polydiethylparaxylylene, and the like can be used.

[0028] According to the radiation image sensor of the present invention, since the scintillator is covered with an elastic organic film and is superposed onto the imaging device with a matching oil interposed therebetween, the impact acting on the scintillator can be alleviated by way of the elastic organic film when superposing the scintillator panel onto the imaging device, whereby the scintillator can be prevented from being damaged. Also, even when a distortion is generated in the substrate due to temperature changes, since the scintillator is covered with the elastic organic film, the stress acting on the scintillator according to the distortion of substrate can be alleviated by the elastic organic film, whereby the scintillator can be prevented from being damaged.

Industrial Applicability

[0029] As in the foregoing, the radiation image sensor in accordance with the present invention is suitably usable for medical and industrial X-ray photography and the like.

Claims

1. A radiation image sensor comprising a scintillator panel and an imaging device;

wherein said scintillator panel comprises a radiation-transparent substrate, a scintillator formed on said substrate, and an elastic organic film covering said scintillator; and wherein said scintillator panel and said imaging device are superposed on each other with an optical coupling material interposed therebetween, side wall portions of said scintillator panel and imaging device being firmly attached to each other with a resin.

2. A radiation image sensor according to claim 1, wherein said scintillator has a columnar structure.

Fig. 1




Fig.2A




Fig.2B




Fig.2C




Fig.3A





Fig.3B



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP99/03263

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl ⁶ G01T1/20		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl ⁶ G01T1/20		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1922-1996 Toroku Jitsuyo Shinan Koho 1994-1999 Kokai Jitsuyo Shinan Koho 1971-1999 Jitsuyo Shinan Toroku Koho 1996-1999		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	Reference 1: JP, 1-240887, A (Hitachi, Ltd.), 26 September, 1989 (26. 09. 89), Full text ; Figs. 1, 4	1, 2
Y	Reference 2: JP, 63-215987, A (Hamamatsu Photonics K.K.), 8 September, 1988 (08. 09. 88), Full text ; Figs. 1, 3	1, 2
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 24 August, 1999 (24. 08. 99)		Date of mailing of the international search report 14 September, 1999 (14. 09. 99)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)